PREMLENE

Name BF-rated Nitrile Rubber Sheet (NBR)

Code NIS-BFSS-B70

Spec ASTM D2000 1BF710

1. DIMENSIONS AND APPEARANCE

Thickness	in	1/32 - 2
Length	ft	5 - 300
Width	in	2 - 72
Surface finishing Colour		Smooth finish, both sides Black

2. PHYSICAL PROPERTIES

Hardness Tensile strength Elongation	Shore A psi (MPa), min %, min	70 ± 5 1000 (6.9) 250	ASTM D2240 ASTM D412 ASTM D412
Heat resistance (100°C, 70h)			
Change in hardness	Shore A, max	± 15	ASTM D573/2240
Change in tensile	%, max	± 30	ASTM D573/412
Change in elongation	%, max	- 50	ASTM D573/412
Oil immersion (#903, 100°C, 70h)	vol%	≤ 60	ASTM D471
Compression set (100°C, 22h)	%, max	50	ASTM D395B
Low working temp	°F	- 30	
High working temp	°F	190	

3. TOLERANCES

TARGET THICKNESS, in (mm)	MINIMUM, mm	MAXIMUM, mm	WIDTH TOLERANCE, in
1/32 (0.8)	0.54	1.05	-0/+1
1/16 (1.6)	1.21	1.97	-0/+1
3/32 (2.4)	2.00	2.76	-0/+1
1/8 (3.2)	2.79	3.56	-0/+1
3/16 (4.8)	3.95	5.58	-0/+1
1/4 (6.4)	5.54	7.16	-0/+1
3/8 (9.5)	8.71	10.34	-0/+1
1/2 (12.7)	11.51	13.89	-0/+1
5/8 (15.9)	14.4	17.48	-0/+1
3/4 (19.1)	16.69	21.41	-0/+1
1 (25.4)	22.86	27.94	-0/+1

GCP Elastomeric Inc. cannot foresee all circumstances under which this information and our products in conjunction with other manufactures products may be used. Physical properties are typical values obtained from sample testing at Akron laboratories or GCP Approved Supplier™ laboratories. Actual production values may vary. It is the users' responsibility to ensure the products are appropriate for their application. We accept no responsibility for results obtained by the application of the information or the safety and suitability of our products, either alone or in combination with other products. If you have any questions in this regard please contact our technical director George Qu (george@gcpindustrial.com).