

Name Commercial Rubber Sheet (SBR)
Code CRS-SS-B65

1. DIMENSIONS AND APPEARANCE

Thickness	in	1/32 - 2
Length	ft	5 - 300
Width	in	2 - 72
Surface finishing		Smooth finish, both sides
Color		Black

2. PHYSICAL PROPERTIES

Hardness	Shore A	65 ± 5	ASTM D2240
Tensile strength	psi (MPa)	435 min.	ASTM D412
Elongation	%	250 min.	ASTM D412
Compression set (70°C, 22h)	%	50 max.	ASTM D395B
Low working temp	°F	-22	
High working temp	°F	180	

3. TOLERANCES

TARGET THICKNESS, in (mm)	MINIMUM, mm	MAXIMUM, mm	WIDTH TOLERANCE, in
1/32 (0.8)	0.54	1.05	-0/+1
1/16 (1.6)	1.21	1.97	-0/+1
3/32 (2.4)	2.00	2.76	-0/+1
1/8 (3.2)	2.79	3.56	-0/+1
3/16 (4.8)	3.95	5.58	-0/+1
1/4 (6.4)	5.54	7.16	-0/+1
3/8 (9.5)	8.71	10.34	-0/+1
1/2 (12.7)	11.51	13.89	-0/+1
5/8 (15.9)	14.4	17.48	-0/+1
3/4 (19.1)	16.69	21.41	-0/+1
1 (25.4)	22.86	27.94	-0/+1

Whitmore Inc. cannot foresee all circumstances under which this information and our products in conjunction with other manufactures products may be used. Physical properties are typical values obtained from sample testing at Akron laboratories or GCP Approved Supplier™ laboratories. Actual production values may vary. It is the users' responsibility to ensure the products are appropriate for their application. We accept no responsibility for results obtained by the application of the information or the safety and suitability of our products, either alone or in combination with other products. If you have any questions in this regard please contact: info@whitmoreinc.com.