

Name **FDA White Neoprene Sheet 60 Duro**  
Code **NES-FDA-SS-650-W60**

### 1. DIMENSIONS AND APPEARANCE

Thickness	in	1/32 - 2
Length	ft	5 - 100
Width	in	2 - 72
Surface finishing		Smooth finish
Color		White

### 2. PHYSICAL PROPERTIES

Hardness	Shore A	60 ± 5	ASTM D2240
Tensile strength	psi	650	ASTM D412
Elongation	%	300	ASTM D412
Compression Set (22h×70°C)	%	35	ASTM D395B
Heat resistance (70h, 100°C)			
Change in Hardness, max	Shore A	7	ASTM D573/2240
Change in Tensile, max	%	-65	ASTM D573/412
Change in Elongation, max	%	-35	ASTM D573/412
Tear strength	N/mm	15	ASTM D624
Low working temp	°F	-22	
High working temp	°F	176	
FDA compliance	FDA approved ingredients, chemically compliant per 21 CFR 177.2600		

### 3. TOLERANCES

TARGET THICKNESS, in (mm)	MINIMUM, mm	MAXIMUM, mm	WIDTH TOLERANCE, in
1/32 (0.8)	0.54	1.05	-0/+1
1/16 (1.6)	1.21	1.97	-0/+1
3/32 (2.4)	2.00	2.76	-0/+1
1/8 (3.2)	2.79	3.56	-0/+1
3/16 (4.8)	3.95	5.58	-0/+1
1/4 (6.4)	5.54	7.16	-0/+1
3/8 (9.5)	8.71	10.34	-0/+1
1/2 (12.7)	11.51	13.89	-0/+1
5/8 (15.9)	14.4	17.48	-0/+1
3/4 (19.1)	16.69	21.41	-0/+1
1 (25.4)	22.86	27.94	-0/+1